










1/1	Categoria	Lac 2K			
	Numar TDS	NO_21_21	Numar de inregistrare	000024104	
	Numar SDS	SDS_NO_3_02	Data intocmirii	28.09.2021	

# ROCK CLEAR 8200

## LAC VHS

PROPRIETATI	<b>TIPOLOGIE VHS</b> <b>INTARITOR HARD 90-800</b> Intaritoare disponibile <b>RAPID, STANDARD, LENT, EXTRA LENT</b>		<b>DESCRIERE:</b> Lac VHS cu un luciu deosebit , modern si duritate superioara. Datorita particulelor solide ( mai mult de 60%) este extreme de eficient. Poate crea efectul OEM- coaja de portocala.				
	PRODUSE COMPLEMENTARE		PLUS 750	PLUS 760	PLUS 770	THIN 890	
	SUBSTRAT	SPECTRAL BASE 2.0 SPECTRAL WAVE 2.0		Se aplica pe straturi uscate de SPECTRAL			
<b>ATENTIE</b>		Lacul este compatibil cu majoritatea vopselurilor pe baza de apa si de solvent de pe piata					
AMESTEC			VOLUM	GREUTATE	Limita VOC II/B/d *	420 g/l	
		<b>ROCK CLEAR 8200</b>	<b>2</b>	<b>100 g</b>	Continut VOC	415 g/l	
		<b>HARD 90-800</b>	<b>1</b>	<b>50 g</b>	* amestecul gata preparat e conform cu UE Directiva 2004/42/CE		
APLICARE		Viscositate DIN 4 in 20°C <b>18-20 s</b>		<b>½ strat + 1 strat</b> Aplicati un strat subtire plin, flash off, aplicati un strat plin ud Grosimea unui singur strat Grosimea maxima a straturilor			30 ÷ 35 µm 70 µm
		Duza: <b>Ø 1.2-1.4 mm</b>		<b>5-10 min / 20°C</b> Depinde de duza Este recomandat sa fie aplicat la o temperature de aprox. 15°C si umiditate nu mai mare de 70%.			
	Urmati instructiunile fabricantului	Presiune: <b>1.7-2.2 bar</b>		<b>STABILITATE</b> <b>30 min / 20°C cu HARD 90-800 FAST,</b> <b>45 min/20°C cu HARD 90-800 STANDARD/SLOW/EXTRA SLOW</b>			
INTARITOR	Marimea/nr. elementelor		15 – 20 °C	20 – 25 °C	25 – 35 °C	+ 35 °C	
	Pete 1-2 parti		HARD 90-800 FAST	HARD 90-800 FAST/STANDARD	HARD 90-800 STANDARD	HARD 90-800 SLOW	
	Zone medii 3-5 parti		HARD 90-800 FAST	HARD 90-800 STANDARD	HARD 90-800 SLOW	HARD 90-800 EXTRA SLOW	
	Zone mari 5-10 parti		HARD 90-800 STANDARD	HARD 90-800 STANDARD	HARD 90-800 SLOW	HARD 90-800 EXTRA SLOW	
	Foarte mari 8 - 13 parti		HARD 90-800 STANDARD	HARD 90-800 SLOW	HARD 90-800 EXTRA SLOW	HARD 90-800 EXTRA SLOW	
USCARE	cu HARD 90-800 STANDARD		20°C	60°C		<b>10 min UNDE SCURTE</b> Incalziti 10 min dupa stratul final la distanta de 50 - 70 cm- temp. max. 90°C	
	Fara praf		30 min	5 min			
	Duritatea intaritorului		10 ore	30 min + 3 ore /20°C			
	Duritate finala		5 zile	30 min + 3 zile / 20°C			
ATENTIE		<b>FOLOSITI ECHIPAMENT DE PROTECTIE</b>	<b>A SE VEDEA FISA DE SECURITATE DOAR PENTRU UZ INDUSTRIAL</b>		<b>VALABILITATE</b> ROCK CLEAR 8200 24 luni /20°C HARD 90-800 STANDARD, SLOW, EXTRA SLOW: 18 luni /20°C FAST: 12 luni /20°C		